



800 Park Drive
Owatonna, MN 55060

800.533.2080
viracon.com

Silicone Compatibility

Viracon utilizes Dow 982, Dow 3365V, or Kommerling GD920 as the secondary sealant in our insulating units. We reserve the right to utilize multiple silicone suppliers for our secondary seal to ensure delivery commitments are met. We cannot commit to utilizing a single supplier.

The following sealants have been found to be compatible with Dow 982, Dow 3365V, and Kommerling GD920: Dow Corning 121, 756, 791, 795 and 983.

Other sealants need to be approved by their respective manufacturer. Acetic acid liberating silicone sealants (acetoxy sealants) must not be used.